

1 (BSP December 2, 2002)  
2 The scarification depth for all concrete decks receiving polyester concrete overlay  
3 shall be 6.35 millimeters, and all references to scarification depth in Sections 6-  
4 09.3(5)A and 6-09.3(5)B shall be revised accordingly.